


SAM™ data sheet SAM-1064-21-x-500fs, $\lambda = 1064 \text{ nm}$

Laser wavelength	$\lambda = 1064 \text{ nm}$
High reflection band (R > 35%)	$\lambda = 990 \dots 1080 \text{ nm}$
Absorbance	$A_0 = 21 \%$
Modulation depth	$\Delta R = 10 \%$
Non-saturable loss	$A_{ns} = 11 \%$
Saturation fluence	$\Phi_{sat} = 53 \mu\text{J}/\text{cm}^2$
Relaxation time constant	$\tau \sim 500 \text{ fs}$
Damage threshold	$300 \text{ MW}/\text{cm}^2$
Chip area	4mm x 4mm; other dimensions on request
Chip thickness	400 μm ; optional: 150 μm on request
Protection	the SAM is protected with a dielectric front layer

Mounting of SAM-1064-21-x-500fs denotes the type of mounting as follows:


x = 0	unmounted
x = 12.7 g	glued on a gold plated Cu-cylinder with 12.7 mm \varnothing
x = 25.4 g	glued on a gold plated Cu-cylinder with 25.4 mm \varnothing
x = 12.7 s	soldered on a gold plated Cu-cylinder with 12.7 mm \varnothing
x = 25.4 s	soldered on a gold plated Cu-cylinder with 25.4 mm \varnothing
x = FC	mounted on a 1 m monomode fiber cable with FC connector

Low intensity spectral reflectance




SAM 472 lb

15.01.2009



Saturation measurement



Pump-probe measurement

