



## SAM™ data sheet SAM-1920-8-x-500fs, $\lambda = 1920$ nm

Laser wavelength	$\lambda = 1920$ nm
High reflection band (R > 91%)	$\lambda = 1850 \dots 1980$ nm
Absorbance	$A_0 = 8$ %
Modulation depth	$\Delta R = 5$ %
Non-saturable loss	$A_{ns} = 3$ %
Saturation fluence	$\Phi_{sat} = 20$ $\mu\text{J}/\text{cm}^2$
Relaxation time constant	$\tau \sim 500$ fs
Damage threshold	500 MW/cm <sup>2</sup>
Chip area	4mm x 4mm; other dimensions on request
Chip thickness	400 $\mu\text{m}$
Protection	the SAM is protected with a dielectric front layer
Mounting of SAM-1920-8-x	denotes the type of mounting as follows:
x = 0	unmounted
x = 12.7 g	glued on a gold plated Cu-cylinder with 12.7 mm $\varnothing$
x = 25.4 g	glued on a gold plated Cu-cylinder with 25.4 mm $\varnothing$
x = 12.7 s	soldered on a gold plated Cu-cylinder with 12.7 mm $\varnothing$
x = 25.4 s	soldered on a gold plated Cu-cylinder with 25.4 mm $\varnothing$
x = FC	mounted on a 1 m monomode fiber cable with FC connector

### Low intensity spectral reflectance



SAM 528 lb



SAM 528 lb